

3M™ Shipping-Mate™ Aerosols for Packaging

	Product	Features	Spray Width	Bonding Range Surfaces One/Both	Relative Adhesion		Temp. Resist. ⁽³⁾	Coverage Sq. Ft./ Cont. ⁽⁴⁾
					Shear ⁽¹⁾ (PSI) Initial/ Ultimate	Peel Strength ⁽²⁾		
Shipping-Mate Aerosols	Case Sealing Adhesive	Ten-second holding strength with carton-tearing strength in 5 minutes. Convenient for shipping room carton closure and warehouse reclosure after inspection.	3"	N/R/15 min.	40/160	N/A	160°F (71°C)	100
	Labeling Adhesive	Clear, fast-tacking. Holds labels to many corrugated cartons and problem surfaces such as glass, plastic and more. Moisture-resistant bond.	2.5"	10 min. / N/R	15/120	N/A	130°F (54°C)	90
	Palletizing Adhesive	Nearly immediate tack permits bags to be stacked on pallets without slipping. Easy separation after shipment. Clear color.	1.5"	10 min. / N/R	10/10	N/A	120°F (49°C)	300
	Box Re-nu Coating	Covers most printing and labels with permanent tan color for reuse of corrugated cartons.	3"	N/A / N/A	N/A / N/A	N/A	250°F (121°C)	25

Note: The technical information and data on these pages should be considered representative or typical only, and should not be used for specification purposes.

N/R = Not recommended
N/A = Not applicable

(1) AdhD T.M. C-700; 1/8" birch veneer bonded to 1/8" birch veneer.
(2) AdhD T.M. C-449.

(3) AdhD T.M. C-483; 500 g load for 1 hr. at noted temp.
(4) All container sizes 24-fl. oz. except Box Re-nu Coating.